

09-27-00

A

09/26/00
JC849 U.S. PTO

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE


JC930 U.S. PTO
09/26/00
09/670181

In re Application)	<u>PATENT APPLICATION</u>
Inventor(s): Alfred Duane Roeske)	
SC/Serial No.: Unknown)	
Filed: Herewith)	
Title: Low-Soot, Low-Smoke Renewable Resource Candle)	

CERTIFICATE OF MAILING BY "EXPRESS MAIL"
UNDER 37 C.F.R. Section 1.10

"Express Mail" mailing label number: EK 810 040 108 US
Date of Mailing: September 25, 2000

I hereby certify that this correspondence is being deposited with the United States Postal Service, utilizing the "Express Mail Post Office to Addressee" service addressed to Commissioner of Patents and Trademarks, Washington, DC 20231 and mailed on the above Date of Mailing with the above "Express Mail" mailing label number.

 (Attorney Signature)
 Steven J. Adamson, Reg. No. 32,776
 Signature Date: September 25, 2000

APPLICATION TRANSMITTAL LETTER

Box PATENT APPLICATION
Commissioner of Patents and Trademarks
Washington, DC 20231

Sir:

Transmitted herewith for filing is the patent application identified as follows:

Inventor(s): Alfred Duane Roeske

Title: Low-Soot, Low-Smoke Renewable Resource Candle

No. of pages of Specification: 14 (plus cover); No. of Claims: 20.

No. of Sheets of Drawings: 1; Informal.

Also enclosed are:

- x A Declaration (unsigned)
- An Assignment and Recordation Form Cover Sheet
- A certified copy of a priority application

09/26/00 09:26:00

- ___ A Power of Attorney
- ___ A Verified Statement to establish small entity status
- ___ An Information Disclosure Statement under 37 C.F.R. Section 1.56.

The filing fee pursuant to 37 C.F.R. Section 1.16 is determined as follows:

No. Filed	No. Extra	Rate Small Entity/ Other Than Small Entity	
Basic		\$345.00	
Fee		\$690.00	= \$ 345.00
Total			\$ 9.00
Claims	<u>20</u> - 20 = <u>0</u> *	X	\$ 18.00 = \$
Independent			\$ 39.00
Claims	<u>3</u> - 3 = <u>0</u> *	X	\$ 78.00 = \$
First Presentation of			\$130.00
Multiple Dependent Claim(s)			\$260.00 = \$ ---
*If the difference is less than zero, enter "0".			Total \$ 345.00

A check in the amount of \$_____ to cover the filing fee is enclosed.


This application is filed pursuant to 37 C.F.R. Section 1.53 in the name of the above-identified Inventor(s).

Please direct all correspondence concerning the above-identified application to:

Steven J. Adamson, PC
P.O. Box 5997
Portland, OR, 97228
Telephone: 503.231.7644

Respectfully Submitted,

Date: 9-25-00


Steven J. Adamson
Reg. No. 32,776

LOW-SOOT, LOW-SMOKE
RENEWABLE RESOURCE CANDLE

15

LOW-SOOT, LOW-SMOKE
RENEWABLE RESOURCE CANDLE

5 Inventor(s): Alfred Duane Roeske

CROSS REFERENCE TO RELATED APPLICATIONS

10 This application claims the benefit of U.S. Provisional Application No. 60/155,848, filed September 24, 1999, and U.S. Provisional Application No. 60/159,062, filed October 12, 1999, both entitled Smoke-Free Renewable Resource Candle and having the inventor(s) listed above.

FIELD OF THE INVENTION

15 The present invention relates to candles and, more specifically, to low-soot, low-smoke, economically priced candles. The present invention also relates to candles made from renewable resource material such as from plant derived material.

20 BACKGROUND OF THE INVENTION

Candles are often made from petroleum based wax such as paraffin wax. Prior to the development of petroleum based waxes, candles were typically made from animal fats such as tallow, etc.

Candles made from either of these two materials are disadvantageous in that they produce an undesirable amount of soot or smoke, darkening ceilings, curtains and other surfaces. Petroleum based candles are further disadvantageous in that they are from a non-renewable source, and animal based candles are objectionable to some people (because they are made from a source that is inefficiently high on the food chain, amongst other reasons).

U.S. Patent no. 1,954,659, issued to Will on August 6, 1934, for a Candle and Method of Making Same, teaches a candle that includes "50% or more vegetable oil combined with paraffin wax, stearic acid, beeswax or other waxes, ...
5 if the vegetable oil, such as rapeseed oil is first hydrogenated." The goal of the Will patent is to process vegetable oil in such a manner as to cause it to change from a liquid to a solid. The type of oil used by Will (e.g., high erucic-content rapeseed) and his
10 "hydrogenation" method achieved a solidification, or "hardening," of the oil. Nonetheless, Will's use of the word "hydrogenation" has a meaning different from hydrogenation as used in the present invention. For example, circa 1930 hydrogenation was carried out using a
15 hydrogenation catalyst that favored both (1) hydrogenation of unsaturated triglyceride fatty acid molecules and (2) isomerization of *cis* ("Z") fatty acid isomers to *trans* ("E") fatty acid isomers. Both (1) and (2) result in an increased melting point, and thus the desired "hardening"
20 of the oil is achieved without fully hydrogenating the unsaturated triglycerides. This in turn results in a candle that is sufficiently hard for its intended purposes, but that creates an undesirable amount of smoke or soot due to unsaturated triglycerides.

25 By circa 1930 standards, it is estimated that the Iodine Value (IV) for hydrogenated ("hardened") rapeseed oil would have been 15 or greater because it is very high in erucic acid (approximately 20% or higher C22 mono-unsaturated fatty acid content). It should be noted that
30 IV measurements are known in the art and IV is a measure of the degree of unsaturation of a fatty acid (whether free or as part of a triglyceride). More information is provided below concerning IVs.

With respect to lower-soot, lower-smoke candles, beeswax has been used to make candles that were purported to be less sooty and smoky than paraffin candles. The process of obtaining beeswax, however, is complicated and time consuming and, therefore, renders beeswax candles disadvantageously expensive. Additionally, modern testing of beeswax candles has shown that while they may have a lower propensity to soot than paraffin candles, it is still undesirably high.

SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide a soot-free, low-smoke candle that is made substantially from renewable resources.

It is another object of the present invention to provide such a candle that is economically priced.

It is also an object of the present invention to provide such a candle that includes hydrogenated plant oils having low IV values.

These and related objects of the present invention are achieved by use of a low-smoke, low-soot renewable resource candle as described herein.

In one embodiment, the present invention includes a candle comprised substantially of hydrogenated plant source triglycerides having an iodine value of less than 10. Other embodiments include a similarly composed candle having an iodine value of 7.5, 5, 3, 1 or 0.5 or less. The triglyceride material may be from plant source material (in whole or in part). A free fatty acid component is preferably provided in combination with the triglyceride material and the concentration of this component may vary. This component may similarly be provided in whole or in part from plant source material. Furthermore, the iodine

value of the free fatty acid material is preferably less than 10, 7.5, 5, 3, 1 or 0.5.

The attainment of the foregoing and related advantages and features of the invention should be more readily apparent to those skilled in the art, after review of the following more detailed description of the invention taken together with the drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a diagram of a candle in accordance with the present invention.

Fig. 2 is a diagram of a triglyceride in accordance with the present invention.

Fig. 3 is a diagram of a free fatty acid in accordance with the present invention.

DETAILED DESCRIPTION

The present invention achieves low-soot, low-smoke candles by virtue in part of using triglycerides and fatty acids that have low Iodine Values (IVs). IV for purposes of the present invention is a measure of the unsaturation of fats and oils and is expressed in terms of the number of centigrams of iodine absorbed per gram of sample (% iodine absorbed). The preferred measurement protocol is Official Method Cd 1d-92 of the American Oil Chemists Society, though other protocols may be used. IVs are an indication of the degree of unsaturation within the triglycerides and/or free fatty acids, and the amount of unsaturated triglycerides and/or fatty acids is proportional to the amount of undesired combustion products (i.e., soot and smoke, etc.). Thus, reducing the level of unsaturation reduces IV and also reduces soot the potential for soot and smoke production.

The present invention includes triglyceride material with IVs below 10 and, for example, includes candles with IVs less than 8,5,3 and 1, etc. In a more preferred embodiment of the present invention, the IV of the triglyceride and fatty acid components are less than one, both individually and in combination.

In the text that follows, various component combinations are disclosed that are directed towards creating an inexpensive, clean burning candle. It should be understood that the component triglycerides and/or free fatty acids have low IVs due to contemporary hydrogenation techniques and capabilities. IVs for various components and hydrogenation consideration are discussed in more detail below.

Referring to Fig. 1, a diagram of a candle in accordance with the present invention is shown. The candle of Fig. 1 (in votive 13 or non-votive form) may include varied components and/or component combinations without departing from the present invention. These varied arrangements include a candle made from:

- I. Plant source triglycerides;
- II. Plant source triglycerides and free fatty acids;
- III. Plant source triglycerides and plant source free fatty acids.

In a preferred embodiment, candle 10 is made of plant source triglycerides (TGs) and plant source free fatty acids (FFAs). Representative chemical structures for these molecules are shown in Fig. 2 and 3, respectively. Preferably, candle 10 is made of palm stearine (the plant source TG) and vegetable-derived stearic acid (a eutectic mix of primarily palmitic and stearic acids) as the FFA.

TG and FFA

5

approximately 4 to 22% FFA by weight.

10

15

20

25

30

While the percentage of TG and FFA will vary based on the container in which the candle is provided (for example with votives), the desired burn characteristics, and to some extent the source of TGs and FFAs, a preferred blend with palm stearine as the TG is approximately 88% TG and 12% FFA by weight. As noted above these percentages may range considerably, from more than 50% FFA to 0% FFA. It should be recognized that currently FFA is relatively more expensive than TG.

While palm stearine and vegetable stearic acid are more preferred, it should be recognized that other TGs and FFAs are suitable and included within the present invention. A partial list of raw material sources for these other TG and FFA raw materials is provided a few paragraphs below. These TGs include those that have a melting point between approximately 110 and 170 degrees F (and it should be recognized that commercial TGs may have small quantities of diglyceride and monoglyceride components). These TGs preferably have highly saturated C16 and/or C18 fatty acid molecules (or predominantly have these molecules) which give the desired melt point.

Triglycerides that contain higher fatty acid homologues, such as C20 and C22 and even C24, would also be usable and would tend to give higher melting points.

Techniques for separating out and hydrogenating triglycerides and fatty acids of specific lengths are known in the art. It should also be recognized that hydrogenated or saturated molecules are preferred because they result in less combustion by-product (i.e., soot, smoke).

Utilizing known separation and hydrogenation techniques (discussed below) any fat, oil or wax that contains relatively high quantities (approximately 50% or greater in total) of C12, C14, C16 and/or C18 fatty acids

in the triglyceride molecule is a suitable source candidate for the triglyceride(s) and/or free fatty acid(s) of the present invention. Thus, in addition to palm oil, the TGs and/or FFAs of the present invention may be derived from the oil of rapeseed, canola, soybean, corn, cottonseed, olive, peanut, perilla, linseed, candlenut, rubberseed, safflower, poppy, walnut, tobacco, niger, sunflower, sesame, meadowfoam, kukui nut, macadamia nut, coconut and cocoa amongst other seeds and/or nuts. It also should be recognized that the FFA may be obtained from animal (e.g., tallow), petroleum or other non-plant sources; additionally, the TGs may be obtained from non-plant sources as well but this is less desirable.

As alluded to above, to affect even better candle burning properties it is advantageous to add a saturated fatty acid such as stearic and/or palmitic acid to the triglyceride candle wax material. It is possible to use a behenic acid (C20), saturated C22 fatty acid, saturated C24 fatty acid, myristic acid (C14) or lauric acid (C12), or a combination of these or other fatty acids. The result is a longer burning, more even burning candle flame that is desirable for a more controlled, modulated burn. Unsaturated fatty acids are not desirable in that they may lead to incomplete combustion and sooting and would also further depress the melting point.

Hydrogenation and IV

The TGs used in the present invention are preferably based on various natural sources previously listed. The oils that are isolated from these natural sources are typically in liquid or semi-solid form and must be hydrogenated to yield the desired solid, waxy material from which a candle can be made. In the case of palm stearine, the starting material is palm oil or palm kernel

5

15

30

09670181-092600

healthful, low smoke, low-soot, renewable (or like) candles are achieved. Lower IVs are achieved with increased substrate processing (i.e., hydrogenation) and increasing processing typically leads to increased cost of substrate material. Thus, a candle with IV of 10 may have a cost that is less than that of a candle having an IV of 7.5, for example, or a candle having an IV of 5. With improvements in hydrogenation processing, however, the efficacy and cost of hydrogenation has decreased. This permits that attainment of TG and/or FFA materials having IVs of 3, 1, 0.5 or less that are still favorable and economically priced. For persons who are most sensitive to combustion products or have other respiratory or soot/smoke sensitive conditions, a candle having an IV of 0.5 to 1 and perhaps up to 3 is going to be preferred. Persons seeking a clean burning candle, yet are less sensitive may prefer a candle with an IV ranging from 3 to 7.5 or the like. Other persons who want a cleaner candle, yet are very cost sensitive may prefer a candle from 7.5 to 10. Note that these criteria include generalizations and material costs may vary based on supply and demand amongst other parameters.

While specific IV values are provided here, it should be recognized that the present inventions contribution of more fully hydrogenated plant source TGs and low soot, low smoke candles should not be limited by a specific number. The present invention is intended to cover candles of all IV below those taught by the prior art, particularly for candles containing plant source TGs.

While the invention has been described in connection with specific embodiments thereof, it will be understood that it is capable of further modification, and this application is intended to cover any variations, uses, or adaptations of the invention following, in general, the

5

CLAIMS

1. A candle comprised substantially of hydrogenated plant source triglycerides having an iodine value of less than 10.

5

2. The candle of claim 1, wherein said iodine value is less than 7.5.

3. The candle of claim 1, wherein said iodine value is less than 5.

10

4. The candle of claim 1, wherein said iodine value is less than 3.

15

5. The candle of claim 1, wherein said iodine value is less than 1.

6. The candle of claim 1, further comprising, in combination with said triglyceride, a free fatty acid.

20

7. The candle of claim 6, wherein said free fatty acid includes a plant source free fatty acid.

8. The candle of claim 6, wherein said plant source triglycerides and said free fatty acid have an iodine value of 5 or less.

25

10. The candle of claim 6, wherein said candle is from 2 to 35% free fatty acid.

30

11. The candle of claim 6, wherein said candle is from 4 to 22 % free fatty acid.

12. A candle comprised at least in part of plant source triglycerides and plant source free fatty acids.

13. The candle of claim 12, wherein said candle is
5 at least 40% plant source triglyceride.

14. The candle of claim 12, wherein said candle is at least 70% plant source triglyceride.

10 15. The candle of claim 12, wherein said candle is at least 4% plant source free fatty acid.

15 16. The candle of Claim 12, having an iodine value of less than 10.

17. The candle of Claim 12, having an iodine value of less than 5.

20 18. The candle of Claim 12, having an iodine value of less than 1.

25 19. A candle comprised substantially of hydrogenated triglycerides and hydrogenated free fatty acids having an iodine value of less than 10.

20. The candle of claim 19, having an iodine value of less than 5.

A low soot, low smoke candle that in one embodiment is made of renewable resource material such as plant source material. The candle may include plant source triglycerides and free fatty acids. The free fatty acids may be plant source or other source. Lower iodine value source materials provide highly saturated triglycerides and free fatty acids that in turn are low soot, low smoke. Iodine values of 10 or less down to 1 and 0.5 or less are taught. Use of agricultural "waste" material provides economically priced source material.

Fig. 3



STEARIC ACID

Fig. 1







Fig. 2

STEARIN(E) a.k.a. triglycerine; glycerol tristearate

009250-78702950

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application) PATENT APPLICATION
)
Inventor(s): Alfred Duane Roeske)
)
SC/Serial No.: Unknown)
)
Filed: Herewith)
)
Title: Low-Soot, Low-Smoke Renewable)
Resource Candle)
)

DECLARATION FOR PATENT APPLICATION

As a below named inventor I hereby declare that my residence, post office address and citizenship are as stated below next to my name; I believe that I am the original, first and sole inventor (if one name is listed below), first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

SMOKE-FREE RENEWABLE RESOURCE CANDLE

the specification of which (check appropriate box):

_____ is attached hereto;

_____ was filed with the above-identified "Filed" date and
"SC/Serial No."

_____ was amended on (or amended through) ____.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment(s) referred to above. I acknowledge the duty to disclose information which is material to the examination of the application in accordance with Title 37, Code of Federal Regulations, Section 1.56.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

(1) Full name of sole
or first inventor: Alfred D. Roeske

(1) Residence: 29821 Jeans Road
Veneta, OR 97487

(1) Post Office Address: same as above

(1) Citizenship: United States of America

(1) Inventor's Signature: _____

(1) Date: _____

005260"TS10/960